



### Kraft Board Technical Data Sheet

GRADE	PlyBond (Joules)	GSM	Bulk	Calliper Micron (MM)	Calliper Inch.	Moisture Contents (%)	Density Gr/Cm <sup>3</sup>	RCT (MD) (Nm/g)
Pine	200 +	180 - 250	1.4 - 1.5	0.35 - 0.38	0.014	7 - 8	6.94	8.0 - 9.0
		300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.97	
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.60	
Cedar	250 +	180 - 250	1.4 - 1.5	0.35 - 0.38	0.014	7 - 8	6.94	9.0 - 10
		300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.97	
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.60	
Teak	300 +	180 - 250	1.4 - 1.5	0.35 - 0.38	0.014	7 - 8	6.94	10.0 - 11.0
		300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.97	
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.60	
Oak	400 +	180 - 250	1.4 - 1.5	0.35 - 0.38	0.014	7 - 8	6.94	11.0 - 12.0
		300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.94	
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.94	
Maple	500 +	180 - 250	1.4 - 1.5	0.35 - 0.38	0.014	7 - 8	6.73	12.0 - 13.0
		300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.55	
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	7.14	
Mahogany	600 +	300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.86	13.0 - 14.0
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.45	
Ivory	700	300 - 350	1.4 - 1.5	0.42 - 0.55	0.017	7 - 8	6.86	14.0 - 15.0
		400 - 450	1.4 - 1.5	0.60 - 0.68	0.023	7 - 8	6.45	
<b>COBB</b>	<i>We can maintain COBB as per your requirement between 100 to 250 in 45 seconds</i>							
<b>COIL WIDTH</b>	<i>Starting with minimum slitted coils in width of 65mm</i>							
<b>DIAMETER</b>	<i>36" INCH TO 48" INCH</i>							
<b>ASH</b>	<i>We can maintain ASH between 8.5% to 10.00%</i>							

**Urvashi Pulp and Paper Mills Pvt. Ltd.**

Plot No - 315/316-1, Nr. Ramdev Chokdi, GIDC, Industrial Estate,  
Ankleshwar Dist. Bharuch, Gujarat 393002, India

Website : - [www.urvashipaper.com](http://www.urvashipaper.com)